

In the Specification:

The paragraph beginning on on page 22, line 18 is amended as follows:

Surfactants in amounts of about 0.5% to about 3% by weight of the composition and preferably about 1.2% to about 11.6% by weight of the composition can be used to facilitate mixing the filler with the epoxy. Suitable surfactants include silanes and non-ionic type surface active agents, available as polyethylene glycol-p-tert-octylphenyl ether under the product name Triton X-100 from Rohm and Haas Co., Philadelphia, PA.. Surfactants are generally prepared by the reaction of octylphenol or nonylphenol with ethylene oxide.